

BONDERITE C-AK 1250

Known as Ridoline 1250

March 2020

PRODUCT DESCRIPTION

BONDERITE C-AK 1250 provides the following product characteristics:

Technology	Industrial Cleaner
Product Type	Alkaline Cleaner
Application	Metal Pre-Treatment

BONDERITE C-AK 1250 is a solid alkaline cleaner based on borate, phosphate and nonionic surfactants for steel, zinc plated steel and aluminium.

Application Areas:

BONDERITE C-AK 1250 is used in spray- and spray/immersion processes. Performance can be increased by adding a suitable cleaning booster.

TECHNICAL DATA

Bulk density, (at 20°C), g/L	~810
pH-value (1% in DI water 20°C)	~11.3

DIRECTIONS FOR USE

Preliminary Statement:

Prior to use it is necessary to read the **Material Safety Data Sheet** for information about precautionary measures and safety recommendations. Also, for chemical products exempt from compulsory labeling, the relevant precautions should always be observed. Please also refer to the local safety instructions and contact Henkel for analytical support.

Bath Make-up:

Fill the tank with warm water, start pumping and add for a volume of 1,000 L:

BONDERITE C-AK 1250	2 to 20 kg
---------------------	------------

Operating Data:

Adjusting the following parameters could be necessary depending on the line conditions.

Total alkalinity:

BONDERITE C-AK 1250	2.0 to 20.0 mL
Temperature	50 to 60°C
Duration of treatment	1 to 5 min
Spray pressure	0.8 to 2.0 bar

Bath Control:

BONDERITE C-AK 1250 solution is controlled by titration of the total alkalinity.

Feed, mL	10 mL
Titrant:	0.1 N hydrochloric or 0.1 N sulfuric acid
End point:	pH 3.6
Indicator:	bromecresolgreen (0.1 % alcoholic solution)

- Cool down bath solution to room temperature and pipette 10 mL bath solution into a clean 300 mL Erlenmeyer-flask.
- Add 50 mL deionized water.
- Add 4 to 5 drops of indicator.
- Titrate the solution with 0.1 N hydrochloric or 0.1 N sulfuric acid.
- The endpoint will be shown by a colour change from blue to yellow (pH: 3.6).
- The consumption of 0.1 N hydrochloric or 0.1 N sulfuric acid in mL is equal to the points of total alkalinity

Replenishing:

For each missing point for a volume of 1,000 L add:

BONDERITE C-AK 1250	1.0 kg
---------------------	--------

Classification:

Please refer to the corresponding **Material Safety Data Sheets** for details on:

Hazards identification

Transport information

Regulatory information

Storage:

Recommended Storage Temperature -15 to 40°C
 Shelf-life, months 18months

ADDITIONAL INFORMATION**Disclaimer****Note:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 0.3

Wang Daeng Industrial Supplies Co.,Ltd. Tel: (038) 337 838-9 Mobile: (081) 564-8315 www.WANGDEX.com

Henkel AG & Co. KGaA
 40191 Düsseldorf, Germany
 Phone: +49-211-797-0

Henkel Corporation USA
 Madison Heights, MI 48071
 Phone: +1-248-583-9300

Henkel (China) Co. Ltd.
 201203 Shanghai, China
 +86.21.2891.8000

For more information, please contact us on www.henkel.com